

# Treatment of the acidic effluent from a copper smelter by flotation tailings

Miroslav Sokić<sup>1</sup>, Dragana Radovanović<sup>2</sup>, Branislav Marković<sup>1</sup>, Jovica Stojanović<sup>1</sup>, Željko Kamberović<sup>3</sup>, Nela Petronijević<sup>1</sup>, Srđan Stanković<sup>1</sup>

<sup>1</sup>Institute for Technology of Nuclear and Other Mineral Raw Materials, Franchet D'Esperey Boulevard 86, Belgrade, Serbia

<sup>2</sup>Innovation Center of the Faculty of Technology and Metallurgy in Belgrade Ltd., Karnegijeva 4, Belgrade, Serbia

<sup>3</sup>University of Belgrade, Faculty of Technology and Metallurgy, Karnegijeva 4, Belgrade, Serbia

## Abstract

Since commissioning in 1961, the copper mine Majdanpek, a part of the Mining and Smelting Complex Bor (RTB Bor), produced approximately 378 million tons of flotation tailings. Semi-quantitative mineralogical analysis of the flotation tailings revealed significant content of carbonate minerals (approximately 20-25 %), indicating high acid neutralization capacity. Also, approximately 70 % of copper is in the form of the oxide mineral cuprite (Cu<sub>2</sub>O). Copper can be easily leached from cuprite by using sulphuric acid. The RTB Bor copper smelter generates 8.7 m<sup>3</sup>h<sup>-1</sup> of extremely acidic waste effluent (142.4 kgm<sup>-3</sup> of sulphuric acid, pH - 0.464) with relatively high concentrations of dissolved metals and metalloids (Cu, Fe, Zn, Pb and As). The effluent is currently treated with hydrated lime. The present study focused on application of flotation tailings as a neutralizing agent for acidic effluents. Laboratory experiments followed by computer simulation of the industrial process showed that 99% of the acid can be neutralized with flotation tailings in a series of six reactors resulting in the final copper concentration of 1.55 gL<sup>-1</sup>. Benefits of the proposed process are: lower environmental impact of the process and reduced costs of neutralization of the acidic effluent from the copper smelter.

**Keywords:** flotation tailings; acidic effluent neutralization; copper leaching

Dostupno na Internetu sa adrese časopisa: <http://www.ache.org.rs/HI/>

TECHNICAL PAPER

UDK: 622-034.3+54.05+66.061

Hem. Ind. **73 (2)** 115-124 (2019)

## 1. INTRODUCTION

Production of mineral concentrates by froth flotation generates huge amounts of waste – flotation tailings. Approximately 99 % of the ore processed in flotation plants becomes flotation tailings [1,2]. Flotation tailings consist mainly of gangue minerals, mostly quartz, pyrite and silicates with low contents of copper and other valuable metals that were not extracted from the ore by froth flotation. Production of copper in the Mining and Smelting Complex Bor (RTB Bor), Serbia, began in 1903. Since then, approximately one billion tons of overburden and flotation tailings were deposited in the proximity of copper mines [3]. There is a growing interest in valorisation of copper from the mining waste of the RTB Bor. Antonijević *et al.* [4] tested leaching of copper from flotation tailings of the copper mine Bor in a glass reactor with addition of ferric chloride in 0.1 M sulphuric acid as an oxidant with the solid - liquid ratio of 1:5. After 30 h of leaching, extraction yield of copper was 88 %. Stevanović *et al.* [5] performed an acid leaching experiment of old flotation tailings from the same copper mine in columns by using 0.01 M sulphuric acid, with or without addition of oxidizing agents at solid - liquid ratio of 1:1. The highest yield of copper of 89.87 % achieved during acid leaching in columns was demonstrated for a sample taken from the depth of 10 m without addition of oxidizing agents. Stanković *et al.* [6] used water rich in acidophilic bacteria and ferric iron obtained from the extremely acidic lake Robule, Serbia,

Korespondencija: Miroslav Sokić, Institute for Technology of Nuclear and Other Mineral Raw Materials, Franchet D'Esperey Boulevard 86, Belgrade, Serbia

E-mail: [m.sokic@itnms.ac.rs](mailto:m.sokic@itnms.ac.rs)

Paper received: 09 October 2018

Paper accepted: 15 April 2019

<https://doi.org/10.2298/HEMIND181009010S>



to leach copper from flotation tailings of the RTB BOR in a shaken flask experiment. The average copper leaching degree was approximately 80 %. Sokić *et al.* [7] performed acid leaching of copper from a copper oxide-sulphide ore excavated from the copper mine Cerovo, a part of the RTB Bor. These authors reported the leaching degree of copper of 73.8 % after 3 h in 0.3 M sulphuric acid solution. Stevanović *et al.* [8] tested acid leaching of copper from overburden of the Cerovo mine, which contains mostly copper oxide minerals, followed by copper extraction by the process of solvent extraction and electrowinning (SX/EW). Recently, Stanković *et al.* [9] tested leaching of copper from Bor flotation tailings in 0.2 M sulphuric acid followed by concentration of the residual copper sulphide minerals by froth flotation. Although the mining waste of the copper mine Bor was extensively studied, such research on wastes from the copper mine Majdanpek is lacking. The copper mine Majdanpek is a part of the RTB Bor. Since commissioning of the mine in 1961, approximately 378 million tons of flotation tailings were generated during the process of froth flotation. According to data provided by the management of this copper mine, the average metal contents in the flotation tailing dump are 770 g t<sup>-1</sup> copper, 0.155 g t<sup>-1</sup> gold and 1.066 g t<sup>-1</sup> silver. Based on these data, it can be calculated that the flotation tailing dump contains approximately 292.000 t of copper, 59 t of gold and 403 t of silver.

The mineral concentrate produced in flotation facilities of the RTB Bor is transferred to the copper smelter. Pure copper is produced by autogenous smelting in a flash smelting furnace and by the matte converting process in a Pierce-Smith converter. Smelting and converting processes generate huge amounts of the waste gas SO<sub>2</sub>. The waste SO<sub>2</sub> is treated in a wet scrubber and a cooling tower for wet gas cleaning. The result of this treatment is generation of wastewater characterized by high contents of free sulphuric acid and toxic metals and metalloids. Radovanović *et al.* [10] published an estimated composition of the wastewater from the smelter. Namely, the smelter generates 8.7 m<sup>3</sup> h<sup>-1</sup> of the waste effluent at the temperature of 55 °C with the concentration of sulphuric acid of 142.4 g L<sup>-1</sup> and concentrations of Cu, Fe<sup>2+</sup>, Zn, Pb and As of 0.53, 0.38, 0.54, 0.45 and 1.37 g L<sup>-1</sup>, respectively. The acidic wastewater from the primary copper production is treated by hydrated lime (Ca(OH)<sub>2</sub>). Due to low price of the lime and its high efficiency, it is widely used for neutralization of acidic effluents. The main disadvantage of this process is generation of huge amounts of sludge, which is considered to be a hazardous waste since it contains toxic elements [11-13].

In this work, usage of the waste material (flotation tailings) was proposed for acid neutralization instead of lime. Benefits of this approach would be lowered costs of the waste effluent neutralization and a lower environmental impact. Flotation tailings are a free and abundant material. Treatment of flotation tailings with acidic effluents results in leaching of residual copper from copper oxide minerals, leading to increased concentration of copper in the leach solution. Dissolved copper can be extracted by solvent extraction and electrowinning (SX/EW) or some other hydrometallurgical process. Production of pure copper from waste materials could generate additional income and contribute to the overall economy of the process. Two acid leaching experiments were conducted at the laboratory scale. The aim of the leaching experiments with the use of sulphuric acid, and sulphuric acid in combination with hydrogen peroxide, was to estimate the total amount of copper available for leaching from oxide and sulphide mineral phases, and to get an insight into kinetics of the leaching process. After initial experiments, the next leaching experiment was performed with the use of acidic solution that corresponds to the effluent from the smelter. Experimental conditions were set according to literature data [4,14-16]. Data obtained during that experiment were used as input parameters for computer simulation of the acid neutralization and copper leaching process at the industrial scale.

## 2. MATERIALS AND METHODS

Approximately 20 kg of flotation tailings were collected at several locations in the flotation tailings dump of the copper mine Majdanpek (RTB Bor, Serbia). Particle size of the flotation tailings was determined as ~37 µm by sieving. Leaching experiments were performed by application of sulphuric acid (MOSS & HEMOSS, Serbia) and sulphuric acid with hydrogen peroxide (MOSS & HEMOSS, Serbia). All chemical were of *p.a.* grade.

## 2. 1. Determination of the copper concentration in the leach solution and chemical and mineralogical characterization of the flotation tailings

Concentration of copper in the leach solution was determined by atomic absorption spectrophotometry (AAS) by using a Perkin Elmer Analyst 300 device (Norwalk, USA). Prior to the AAS chemical analysis, solid samples of the flotation tailings were dissolved in *aqua regia*. Mineralogical characterization of the tailings was performed by optical microscopy and XRD (X-Ray Diffraction) methods. A polarizing microscope Carl-Zeiss, model "JENAPOL-U" (Germany) equipped with 10×, 20×, 50×, 100× (oil immersion) objectives and a system for photomicrography ("Axiocam105 colour" camera and "Carl Zeiss AxioVision SE64 Rel. 4.9.1." software package with „Multiphase" module, Carl Zeiss, Germany) was used for morphological investigations in reflected light. X-ray diffraction (XRD) patterns were obtained by using a Philips PW-1710 automated diffractometer (Philips, Netherlands) equipped with a Cu tube operated at 40 kV and 30 mA. The instrument was equipped with a diffracted beam curved graphite monochromator and Xe-filled proportional counter. Diffraction data were collected in the  $2\theta$  Bragg angle range of 4–65°, counting for 1 s. Semi-quantitative analysis of the data obtained by XRD was performed by "Powder Cell" computer software (Federal Institute for Materials Research and Testing, Germany) [17].

## 2. 2. Leaching experiments

Leaching experiments were performed in a 2 L glass reactor equipped with a stirrer, thermometer and funnel for addition of the sample. Temperature control of the reactor was provided by a heating mantle (Electrothermal, UK). Total volume of the leaching solution was 1.2 L. In the first leaching experiment, the concentration of sulphuric acid was 1 M, temperature 80 °C, stirring speed 300 rpm, duration of the experiment 240 min and the quantity of the flotation tailings sample was 20 g (yielding the solid to liquid mass ratio S:L = 1:60). The second leaching experiment was performed with addition of H<sub>2</sub>O<sub>2</sub> as the oxidant. Experimental conditions were: total volume of the leaching solution 1.2 L, the concentration of sulphuric acid 1M, temperature 40 °C, stirring speed 115 rpm, duration of the experiment 240 min, and the quantity of the flotation tailings sample 20 g (yielding the solid to liquid mass ratio S:L = 1:60). Total amount of the 30 wt.% hydrogen peroxide solution was 122 mL. Half of the solution was added after 30 min and the other half after 120 min of the experiment. The third experiment simulated copper leaching by the acidic effluent from a smelter: the volume of leaching solution was 1.2 L, the concentration of sulphuric acid was 1.45 M, temperature was 55 °C, stirring speed 300 rpm, and the experiment duration was 240 min. The solid to liquid mass ratio was 1:5 (240 g of tailings was added to 1.2 L of the acidic solution).

## 2. 3. Computer simulation of the smelter effluent neutralisation by flotation tailings

Simulation of the copper smelter effluent neutralisation process by using flotation tailings was conducted by "SuperPro Designer" software version 6.0 (Intelligen Inc, US). The aim of the simulation was to evaluate the feasibility of the treatment process. Input data for the simulation were: projected amount and composition of the effluent [10,18], calculated amount of flotation tailings to obtain the mass solid to liquid ratio of 1:5 in reactors and the chemical composition of the tailings. The expected simulation outputs were amounts and compositions of the liquid phase – treated wastewater, and the solid phase – components of the tailings, which were not leached by sulphuric acid. Possible reactions during the treatment process and thermodynamic data were determined by the HSC Chemistry software version 6.12 (Outotec Research Oy, Finland) [19]. The necessary number of reactors for acid neutralization was determined from the requirement to obtain a solution with a pH value of 2, suitable for further copper valorisation, with the defined solid to liquid ratio.

## 3. RESULTS AND DISCUSSION

### 3. 1. Results of the chemical and mineralogical characterization of flotation tailings

Results of the chemical characterization of the flotation tailings used in this work (the copper mine Majdanpek) are presented in Table 1.





### 3. 2. Acid leaching experiments

Results of the leaching experiments are presented in Figures 4-6. Based on the measured copper concentrations in tailings by AAS, the leaching degree was calculated by the equation:

$$\text{Leaching degree} = \frac{c_{\text{Cu(l)}} V}{m_{\text{(s)}} mf_{\text{Cu(s)}}} 100 \quad (1)$$

where  $c_{\text{Cu(l)}}$  is the mass concentration of copper in the leach solution,  $V$  is the volume of the leach solution,  $m_{\text{(s)}}$  is the mass of the solid sample, and  $mf_{\text{Cu(s)}}$  is the copper mass fraction in the solid sample.

Course of the leaching experiment with 1M sulphuric acid is presented in Figure 4, that with 1 M sulphuric acid and 1 M hydrogen peroxide in Figure 5 and that with the acidic solution containing 1.45 M sulphuric acid and corresponding to the effluent from a smelter is shown in Figure 6.




Figure 4. Extraction of copper during leaching with 1 M sulphuric acid, S:L = 1:60




Figure 5. Extraction of copper during leaching with 1 M sulphuric acid and 1 M hydrogen peroxide, S:L = 1:60




Figure 6. Extraction of copper during leaching with 1.45 M sulphuric acid, S:L = 1:5 simulating the smelter effluent

Effects of the composition of the leaching acidic solution as well as the solid to liquid mass ratio are clearly visible so that the highest copper extraction yield of ~66 % is obtained in the solution of sulphuric acid with addition of hydrogen peroxide at the S:L ratio of 1:60 (Fig. 5).

### 3. 3. Microscopic analysis of the leaching residue after leaching with addition of hydrogen-peroxide

Solid residue after the second leaching experiment with addition of hydrogen peroxide was examined by optical microscopy. Minerals identified in the residue were: pyrite, magnetite, rutile, chalcopyrite, elemental sulphur and

gangue minerals. Chalcopyrite was present as inclusions in pyrite and quartz (Figs. 7 and 8). Figure 9 shows partially dissolved pyrite after leaching with addition of H<sub>2</sub>O<sub>2</sub>. Copper oxide minerals were not detected in the sample.




Figure 7. Inclusions of chalcopyrite (Ccp) in quartz




Figure 8. Inclusions of chalcopyrite (Ccp) in pyrite (Py)




Figure 9. Partially dissolved pyrite (Py) after leaching with addition of H<sub>2</sub>O<sub>2</sub>

### 3. 4. Computer simulation of neutralisation of the acidic effluent by using flotation tailings

The scheme presented in Figure 10 presents the computer simulation model of the acidic effluent neutralization process by using flotation tailings.




Figure 10. Scheme of the process acidic effluent neutralization by flotation tailings used for computer simulation: the process consists of 6 serially connected reactors each followed by a phase separator; the process contains 19 streams in total

Inputs in the simulation were compositions of wastewater from the copper smelter (acidic effluent) and Majdanpek flotation tailings (Table 2). The chemical composition of the acidic effluent was determined previously by Radovanović *et al.* [10].

Table 2. Compositions of the acidic effluent and flotation tailings as inputs in the simulation (data reprinted from [10] with permission of The Organizing Committee of the 47th International October Conference on Mining and Metallurgy, 4th – 6th October 2015)

Acid effluent		Flotation tailings	
Component	Content, wt. %	Component	Content, wt. %
H <sub>3</sub> AsO <sub>4</sub>	0.26	Al <sub>2</sub> SiO <sub>5</sub>	4.00
Cu	0.07	CaCO <sub>3</sub>	10.00
CuS	0.35	Cu <sub>2</sub> O	0.06
CuSO <sub>4</sub>	0.11	CuFeS <sub>2</sub>	0.03
FeSO <sub>4</sub>	0.21	K <sub>2</sub> SiO <sub>3</sub>	2.00
PbO	0.02	MgCO <sub>3</sub>	10.00
PbSO <sub>4</sub>	0.20	FeS <sub>2</sub>	19.00
PbS	0.08	SiO <sub>2</sub>	54.78
H <sub>2</sub> SO <sub>4</sub>	13.41	ZnS	0.13
H <sub>2</sub> O	85.06		
ZnSO <sub>4</sub>	0.22		

The acidic effluent is formed by mixing wastewater streams generated in wet scrubbers treating gases originating from smelting and converting processes in the copper smelter. It is characterized by a high acid content accompanied with dissolved metals, present as sulphates, as well as dispersed insoluble particles, being metallic or sulphides (Table 2). Flotation tailings, besides the gangue material, also contain carbonates (calcite and dolomite) that could be used for acid neutralization, and copper oxide mineral (cuprite), which can be dissolved by sulphuric acid. Possible reactions that occur during the treatment, and thermodynamic data for enthalpy changes ( $\Delta H$ ), entropy changes ( $\Delta S$ ) and changes in the Gibbs free energy ( $\Delta G$ ) were determined by the HSC Chemistry software and presented in Table 3.

Table 3. Thermodynamic data for possible reactions during the acidic effluent treatment at 25 °C; changes in enthalpy ( $\Delta H$ ), entropy ( $\Delta S$ ) and the Gibbs free energy ( $\Delta G$ )

No.	Reactions	$\Delta H$ / kJ	$\Delta S$ / J K <sup>-1</sup>	$\Delta G$ / kJ
1.	CaCO <sub>3</sub> (s) + 2H <sup>+</sup> + SO <sub>4</sub> <sup>2-</sup> = CaSO <sub>4</sub> (s) + H <sub>2</sub> O(l) + CO <sub>2</sub> (g)	-0.965	278.617	-84.035
2.	MgCO <sub>3</sub> (s) + 2H <sup>+</sup> + SO <sub>4</sub> <sup>2-</sup> = MgSO <sub>4</sub> (s) + H <sub>2</sub> O(l) + CO <sub>2</sub> (g)	64.257	290.145	-22.250
3.	Cu <sub>2</sub> O(s) + 2H <sup>+</sup> + SO <sub>4</sub> <sup>2-</sup> = 2Cu <sup>2+</sup> + SO <sub>4</sub> <sup>2-</sup> + H <sub>2</sub> O(l)	-68.290	-22.580	-62.123

Table 3 shows that all three reactions are possible due to negative values of  $\Delta G$ , and that reactions of acid neutralization (reaction 1) and copper leaching (reaction 3) are exothermic (negative values of  $\Delta H$ ) resulting in the temperature increase. Descriptions of process streams, presented in Figure 10, are given in Table 4.

Table 4. Description and flowrates of process streams in the simulation

Stream	Characteristic	Place in simulation	Flowrate	Stream	Characteristic	Place in simulation	Flowrate
1	Flotation tailings	Input	1073 kg h <sup>-1</sup>	11	Flotation tailings	Input	1073 kg h <sup>-1</sup>
2	Acid effluent	Input	8700 L h <sup>-1</sup>	12	Solution	Transfer	8798 L h <sup>-1</sup>
3	Solution	Transfer	8647 L h <sup>-1</sup>	13	Solid residue	Output	1261 kg h <sup>-1</sup>
4	Solid residue	Output	1329 kg h <sup>-1</sup>	14	Flotation tailings	Input	1073 kg h <sup>-1</sup>
5	Flotation tailings	Input	1073 kg h <sup>-1</sup>	15	Solution	Transfer	8315 L h <sup>-1</sup>
6	Solution	Transfer	8564 L h <sup>-1</sup>	16	Solid residue	Output	1261 kg h <sup>-1</sup>
7	Solid residue	Output	1261 kg h <sup>-1</sup>	17	Flotation tailings	Input	442 kg h <sup>-1</sup>
8	Flotation tailings	Input	1073 kg h <sup>-1</sup>	18	Solution	Output	8254 L h <sup>-1</sup>
9	Solution	Transfer	8481 L h <sup>-1</sup>	19	Solid residue	Output	519 kg h <sup>-1</sup>
10	Solid residue	Output	1261 kg h <sup>-1</sup>				

The acidic effluent enters the process as the stream 2 at the flowrate of  $8700 \text{ L h}^{-1}$ , and is neutralized by addition of  $1073.31 \text{ kg h}^{-1}$  of flotation tailings into each of the five reactors (Streams 1, 5, 8, 11 and 14) and  $442.00 \text{ kg h}^{-1}$  into the sixth reactor (Stream 17) to achieve the pH value of 2 in the output solution (Stream 18). Solid and liquid phases are separated in phase separator after each reactor and solid residues exit the process as output Streams 4, 7, 10, 13, 16 and 19. After the phase separation, the obtained solutions are transferred to the next reactor. The main output from the simulation is Stream 18 with the final copper concentration of  $1.55 \text{ g L}^{-1}$  and the sulphuric acid concentration that corresponds to the pH value of 2.

### 3. 5. Discussion

Results of the first leaching experiment with 1 M sulphuric acid revealed that most of the copper that was extracted in total in this experiment (84 %) was dissolved during the first five minutes of leaching; the total copper extraction degree after 240 min was 51.6 %. Other authors also reported fast dissolution of copper (85 % of totally extracted) from copper oxide minerals during first five minutes of leaching with sulphuric acid [15]. Copper from copper sulphide minerals can be extracted by addition of oxidizing agents [16,20]. Copper extraction increased to 66% after addition of 1 M hydrogen peroxide (Fig. 5). Microscopic analysis of the leaching residue (Figs. 7, 8, 9) showed that most of chalcopyrite minerals were not dissolved after this leaching process. Chalcopyrite was mostly present as inclusions in quartz and pyrite, and, as a consequence, unavailable for leaching, as well as concentration by froth flotation. At the industrial level, hydrogen peroxide would increase costs of the process, and the obtained increase in the copper extraction degree would probably not justify the additional costs. Therefore, it was decided to continue leaching experiments with sulphuric acid only, which is available free as a waste effluent from the smelter.

The aim of the next experiment was to simulate acid neutralization and copper leaching on the industrial scale by using a solution with the sulphuric acid concentration and temperature corresponding to smelter acidic effluents with the solid to liquid mass ratio of 1:5. Again approximately 85 % of the totally extracted copper in this process was leached after five minutes of the experiment. The copper leaching degree was lower in this experiment as it reached 33.5 % after 240 min, due to S:L. Copper oxide minerals, which account for 70 % of the total copper minerals in flotation tailings samples, are readily soluble in acidic solutions. This fact explains the observed rapid increase in the copper concentration at the beginning of the experiment. Accordingly, copper oxide minerals were not detected by the microscopic examination of the solid residue after leaching.

Results of the chemical and mineralogical analysis of the tailings and data obtained by the leaching experiment with 1 M sulphuric acid were used as input parameters for computer simulation of the process at the industrial scale. According to data obtained by simulation,  $5808 \text{ kg h}^{-1}$  of flotation tailings is required to neutralize  $8.7 \text{ m}^3 \text{ h}^{-1}$  of the acidic effluent from the smelter to the pH value of 2 in the series of six agitation tanks. The final concentration of copper at the output from the sixth reactor is  $1.55 \text{ g L}^{-1}$ , indicating that the resulting solution is suitable for extraction of copper by the SX/EW technology. The final concentration of copper is achieved by combining copper contained in the acidic effluent ( $0.53 \text{ g L}^{-1}$ ) and copper extracted from flotation tailings ( $1.02 \text{ g L}^{-1}$ ).

The conventional method for neutralization of the acidic effluent is application of hydrated lime. Radovanović *et al.* [10] performed computer simulation of neutralization of the acidic effluent from the RTB Bor copper smelter by this component. Neutralization of  $8.7 \text{ m}^3 \text{ h}^{-1}$  of the acidic effluent was predicted to generate over  $10 \text{ t h}^{-1}$  of the hazardous sludge and consume approximately  $7 \text{ m}^3 \text{ h}^{-1}$  of the hydrated lime solution. On the contrary, neutralization by using flotation tailings is predicted to produce nearly  $7 \text{ t h}^{-1}$  of the solid residue, which can be deposited in flotation tailings dumps. It should be noted that safe deposition of the voluminous sludge predicted in the first process is a serious environmental issue [11-13]. Obviously, the usage of flotation tailings instead of lime decreases the overall amount of the waste in the process and reduces water consumption, resulting in a decreased environmental impact of the proposed process as compared to the acid neutralization by lime.

According to data obtained by computer simulation, instead of losing copper [21], approximately 100 t of copper could be produced annually by the proposed process. In the software simulation, the leaching duration in each reactor was set to 1 h. Laboratory experiments showed that 85 % of the extractable copper was obtained during the first five

minutes. By decreasing the leaching time in each reactor, improved process efficiency can be achieved as even more copper can be produced during the same time interval.

#### 4. CONCLUSION

Flotation tailings of the copper mine Majdanpek exhibited a good acid neutralization capacity due to the relatively high content of carbonate minerals. Results presented in this paper show that these flotation tailings can be used instead of hydrate lime for neutralization of acidic effluents from the copper smelter of RTB Bor. The environmental impact of the proposed process is lower in comparison to the acid neutralization by using lime. The computer simulation showed that copper present as copper oxide minerals and leached by sulphuric acid could be concentrated up to  $1.55 \text{ g L}^{-1}$  in a series of six reactors. The predicted copper concentration in the pregnant leach solution is suitable for copper extraction by the SX/EW technology. The proposed process for neutralization of acidic effluent from copper smelters by using flotation tailings can lead to cheaper and cleaner production of copper in the RTB Bor and contribute to a circular economy by copper valorisation instead of its loss in flotation tailings and the acidic effluent.

*Acknowledgments.* This work was realized in the frame of projects TR 34033 and TR 34023, supported by the Ministry of Education, Science and Technological Development of the Republic of Serbia.

#### REFERENCES

- [1] Brierley C, Brierley J. Progress in bioleaching part B: applications of microbial processes in the minerals industries, *Appl Microbiol Biotechnol.* 2013; 97: 7543-7522.
- [2] Dold B. Sustainability in metal mining: from exploration, over processing to mine waste management, *Rev Environ Sci Biotechnol.* 2008; 7: 275-285.
- [3] Bogdanović G, Trumić M, Trumić M, Antić DV. Mining waste management – Genesis nad possibilities for processing, *Reciklaža i održivi razvoj* 2011; 4: 37-43 (in Serbian)
- [4] Antonijević MM, Dimitrijević MD, Stevanović ZO, Serbula SM, Bogdanović GD. Investigation of the possibility of copper recovery from the flotation tailings by acid leaching, *J Hazard Mater.* 2008; 158: 23-34.
- [5] Stevanović Z, Antonijević M, Bogdanović G, Bugarin M, Trujić V, Marković R, Nedeljković D. The effect of oxidants through a tailing dump depth and the leaching of copper, *Carpath J Earth Env.* 2013; 8 (1): 29-38.
- [6] Stanković S, Morić I, Pavić A, Vojnović S, Vasiljević B, Cvetković V. Bioleaching of copper from samples of Old flotation tailings (Copper mine Bor, Serbia), *J Serb Chem Soc.* 2015; 80 (3): 391-405.
- [7] Sokić M, Milošević V, Stanković V, Matković V, Marković B. Acid leaching of oxide-sulphide copper ore priore the flotation – A way for increased metal recovery, *Hem Ind.* 2015; 69(5):453-458.
- [8] Stevanović Z, Antonijević M, Jonović R, Avramović Lj, Marković R, Bugarin M, Trujić V. Leach SW-EX copper revalorization from overburden of abandoned copper mine Cerovo, eastern Serbia, *J Min Metall.* 2009; 45 B (1): 45-57.
- [9] Stanković V, Milošević V, Milićević D, Gorgievski M, Bogdanović G. Reprocessing of the old flotation tailings deposited on the Bor tailings pond – A case study, *Chem Ind Chem Eng Q.* 2018; DOI: 10.2298/CICEQ170817005S
- [10] Radovanović D, Kamberović Ž, Ranitović M, Korać M, Gavrilovski M, Mihajlović A. Integral treatment of copper smelter wastewater by copper mine overburden, *47th International October Conference on Mining and Metallurgy*, Bor, Serbia, 2015; 401-404.
- [11] Dimitrijević MD, Alagić SČ. Passive treatment of the acid mine drainage, *Bakar* 2012;37 (1): 58-68. (in Serbian)
- [12] Dimitrijević M., Nujkić MM, Milić SM Treatment of the acid mine drainage with lime, *Bakar* 2012;37 (1): 45-55. (in Serbian)
- [13] Ivišić-Bajčeta D, Kamberović Ž, Korać M, Gavrilovski M. Soolidification/stabilization process of wastewater treatment sludge from primary copper smelter. *J Serb Chem Soc.* 2013; 78(5):725-739.
- [14] Antonijević MM, Janković ZD, Dimitrijević MD. Kintetics of chalcopyrite dissolution by hydrogen peroxide in sulphuric acid, *Hydrometallurgy* 2014; 71 (3-4):329-334.
- [15] Habbache N, Alane N, Djeard S, Tiofuti L. Leaching of copper oxide with different acid solutions, *Chem Eng J.* 2009;152: 503-508.
- [16] Sokić M. Leaching mechanism of polymetallic Pb-Zn-Cu concentrates with sulphuric acid in the presence of selected oxidants, Doctoral dissertation, University of Belgrade, Faculty of Technology and Metallurgy, 2008. (in Serbian)
- [17] Kraus W, Noize G. POWDER CELL - a program for the representation and manipulation of crystal structures and calculation of the resulting X-ray powder patterns, *J Appl Cryst.* 1996; 29: 301-303.
- [18] Radovanović D. Stabilization And Solidification Process Of Hazardous Sludge Generated During Wastewater Treatment Process In Primary Copper Smelter, Doctoral dissertation, University of Belgrade, Faculty of Technology and Metallurgy, 2018. (in Serbian)
- [19] Outotec's HSC Chemistry 6, <https://www.outotec.com/products/digital-solutions/hsc-chemistry/>, accessed 3.11.2017.



- [20] Watling H. Chalcopyrite hydrometallurgy at atmospheric pressure: 1. Review of acidic sulfate, sulfate–chloride and sulfate–nitrate process options., *Hydrometallurgy*, 2013;140: 163-180.
- [21] Ivišić-Bajčeta D, Kamberović Ž, Rogan J, Ćirković M, Pavlović T. Analysis of copper losses through acid effluent flows generated during off-gas treatment in the new copper smelter of RTB Bor, *Metall Mater Eng.* 2013;19: 217-231.

## SAŽETAK

### Tetman kiselih otpadnih voda iz topionice bakra flotacijskom jalovinom

Miroslav Sokić<sup>1</sup>, Dragana Radovanović<sup>2</sup>, Branislav Marković<sup>1</sup>, Jovica Stojanović<sup>1</sup>, Željko Kamberović<sup>3</sup>, Nela Petronijević<sup>1</sup>, Srđan Stanković<sup>1</sup>

<sup>1</sup>Institut za tehnologiju nuklearnih i drugih mineralnih sirovina, Bulevar Franša D'Eperea 86, 11000 Beograd

<sup>2</sup>Inovacioni centar Tehnološko-metalurškog fakulteta doo, Karnegijeva 4, 11000 Beograd

<sup>3</sup>Univerzitet u Beogradu, Tehnološko-metalurški fakultet, Karnegijeva 4, 11000 Beograd

(Stručni rad)

Od otvaranja 1961. g. rudnik bakra Majdanpek (deo RTB Bor) je proizveo približno 378 miliona tona flotacijske jalovine. Iako su koncentracije vrednih metala (bakra, cinka, zlata i srebra) u jalovini veoma male, ukupna količina metala deponovanih u jalovini je značajna. Zbog malih koncentracija, valorizacija metala iz ove flotacijske jalovine nije bila ekonomski opravdana. Semi-kvantitativnom mineraloškom analizom uzoraka flotacijske jalovine utvrđeno je da jalovina sadrži znatne količine karbonatnih minerala (približno 20-25%), što ukazuje na to da ova jalovina ima značajan kapacitet za neutralizaciju kiseline. Oko 70 % bakra prisutnog u jalovini je u obliku oksidnog minerala kuprita (Cu<sub>2</sub>O). Bakar se lako može izlužiti iz kuprita pomoću sumporne kiseline. Topionica bakra RTB Bor proizvodi 8,7 m<sup>3</sup>h<sup>-1</sup> izuzetno kisele otpadne vode (142,4 kgm<sup>-3</sup> sumporne kiseline, pH = -0,464) sa relativno velikim koncentracijama rastvorenih metala i metaloida (Cu, Fe, Zn, Pb i As). Otpadna voda se tretira hidratisanim krečom. U ovom radu je ispitana mogućnost primene flotacijske jalovine u cilju neutralizacije kiselosti otpadne vode uz istovremeno luženje bakra prisutnog u jalovini. Laboratorijski eksperimenti i softverska simulacija su pokazali da je primenom flotacijske jalovine moguće neutralisati 99 % sumporne kiseline u seriji od šest reaktora sa mešanjem. Rezultati dobijeni softverskom simulacijom pokazuju da bi konačna koncentracija bakra u rastvoru nakon postupka neutralizacije bila 1,55 gL<sup>-1</sup>, što bi omogućilo izdvajanje čistog bakra tehnologijom solventne i elektrolitičke ekstrakcije. Prednosti ovog postupka su: manji uticaj na životnu sredinu i niži troškovi postupka neutralizacije kisele otpadne vode iz topionice bakra.

*Ključne reči: flotacijska jalovina, neutralizacija kiselih otpadnih voda, luženje bakra*